

## APPLICATION FOR PATENT

**INVENTORS:** VIRGILIO GO BONCAN, MURRAY J. ROGERS,  
THOMAS HEINOLD, AND ROBERT L. DILLENBECK

**TITLE:** TESTING APPARATUS AND METHOD OF DERIVING  
YOUNG'S MODULUS FROM TENSILE  
STRESS/STRAIN RELATIONSHIPS

### SPECIFICATION

#### Field of the Invention

The invention relates to testing methods and devices used for testing of the mechanical properties of cement including cement formed in wellbore environments.

#### 5 Background of the Invention

Cement is used in the casing and liners of a wellbore. The annular space between the casing/lining and the wellbore is filled with a predetermined quantity of a cement mixture, which after hardening retains the casing/liner in place in the wellbore. The cement mixture is pumped in at the top end of the casing or liner,  
10 down to the lower end thereof and out into and up the annular space on the outside of the casing/liner.

Cementing is employed during many phases of wellbore operations. For example, cement may be employed to cement or secure various casing strings and/or liners in a well. Cementing may also be used to repair casing and/or to achieve  
15 formation isolation. Additionally, cementing may be employed during well abandonment. Cement operations performed in wellbores under these high stress conditions present problems including difficulty in obtaining wellbore isolation and maintaining the mechanical integrity of the wellbore.

In essence, cement is placed in the annulus created between the outside surface of a pipe string and the inside formation surface or wall of a wellbore in order to form a sheath to seal off fluid and/or solid production from formations penetrated by the wellbore. Cementing allows a wellbore to be selectively completed to allow  
5 production from, or injection into, one or more productive formations penetrated by the wellbore. Cement may be used for purposes including sealing off perforations, repairing casing leaks, plugging back or sealing off the lower section of a wellbore, or sealing the interior of a wellbore during abandonment operations.

Once established, this isolation may be impacted by the particular stresses  
10 associated with the environment found in the wellbore during operations. The cement sheath may be exposed to stresses imposed by well operations such as perforating, hydraulic fracturing, or high temperature-pressure differentials.

Furthermore, well cement compositions may be brittle when cured. These cement compositions may fail due to tensional and compressional stresses that are  
15 exerted on the set cement. These wellbore cements may be subjected to axial, shear, and compressional stresses. Relatively high temperatures may induce stress conditions and/or relatively high fluid pressures encountered inside cemented wellbore pipe strings during operations such as perforating, stimulation, injection, testing, or production. Moreover, stress conditions may be induced or aggravated by  
20 fluctuations or cycling in temperature or fluid pressures during similar operations. In addition, variations in temperature and internal pressure of the wellbore pipe string may result in radial and longitudinal pipe expansion and/or contraction which tends to place stress on the annular cement sheath existing between the outside surface of a pipe string and the inside formation surface or wall of a wellbore. In other cases,  
25 cements placed in wellbores are subjected to mechanical stress induced by vibrations and impacts resulting from operations.

Therefore, a need exists to be able to test the mechanical properties of cement such as the cement that is used in wellbore environments. This testing method needs

to be able to accommodate the conditions that are found in the wellbore environment. The following testing method fail to provide a method of testing under these conditions.

Several testing methods have been developed to test various aspects of cement or concrete. For example, ASTM International has established the Standard Test Method for Flexural Strength of Concrete (Using Simple Beam With Center-Point Loading), Designation No. C 293-02. This test method purports to cover the determination of the flexural strength of concrete specimens by the use of a simple beam with center-point loading. The mechanism in this test employs a load-applying block and two specimen support blocks. Force is applied perpendicular to the face of the specimen until the specimen fails. The modulus of rupture is calculated as:

$$R = 3 PL/2bd^2 \quad (1)$$

where:

R = Modulus of rupture, psi, or MPa,

P = maximum applied load indicated by the testing machine, lbf, or N,

L = span length, in., or mm,

b = average width of the specimen at the fracture, in., or mm, and

d = average depth of the specimen at the fracture, in., or mm.

This testing method only provides a modulus of rupture based on a perpendicular force being applied in surface ambient conditions. This testing method therefore fails to simulate the stresses encountered in the higher temperature and pressure conditions of the wellbore environment.

Additional standards have been developed for testing cement. For example ASTM International Standard Test Method for Flexural Strength of Hydraulic-Cement Mortars, Designation No. C 348-02 provides a centerpoint loading such that forces are applied to the specimen in a vertical direction to determine the flexural strength from the total maximum load as follows:

$$S_f = 0.0028 P \quad (2)$$

where

$S_f$  = flexural strength, Mpa, and

$P$  = total maximum load, N.

This testing method only provides a flexural strength based on a vertical force being applied in surface ambient conditions to cause a total maximum load. This testing method therefore also fails to simulate the stresses encountered in the higher temperature and pressure conditions of the wellbore environment.

The standards also include a testing method to measure splitting tensile strength. For example ASTM International Standard Test Method for Splitting Tensile Strength of Cylindrical Concrete Specimens, Designation No. C 496-96 provides for applying a diametrical compressive force along the length of a cylindrical concrete specimen until failure of the specimen. The loading induces tensile stresses on the plane containing the applied load and relatively high compressive stresses in the area around the applied load. Tensile failure occurs rather than compressive failure because the areas of load application are in a state of triaxial compression. The splitting tensile strength of the specimen is calculated by the formula:

$$T = 2P/(\pi l d) \quad (3)$$

where:

$T$  = Tensile splitting strength, psi (kPa),

$P$  = maximum applied load indicated by the testing machine, lbf (kN),

$\pi = 3.1416$

$l$  = length, in. (m), and

$d$  = diameter, in. (m).

Similarly to the previously discussed testing methods, this testing method only provides a tensile splitting strength based on a diametrical compressive force applied in surface ambient conditions. This testing method therefore fails to simulate

the stresses encountered in the higher temperature and pressure conditions of the wellbore environment.

Additionally, each of these standards specifically instructs the creation of the specimens at a temperature and pressure that is similar to ambient surface conditions.

5 None of these testing methods provides for the creation of samples under the temperature and pressure conditions found in a wellbore environment.

Therefore a need exists for the formation and testing of cement under a simulation of the conditions found in a wellbore environment. Testing methods under these conditions will provide data that is more precise in providing for a  
10 method to determine the mechanical characteristics of the specimen.

### **Summary of the Invention**

Most cements fail in the annulus of a well while under tension or a combination of tension and compression (flexural stress). The ratio of axial stress to  
15 axial strain (Young's Modulus) needs to be examined when the axial stress is tensional or a combination of tension and compression.

The present invention offers a method of testing and a tester designed to test the stress and strain of cements under the temperature and pressures encountered by cement during use in wellbore environments. Using these stress and strain  
20 measurements, the Young's Modulus may be established for a material at the encountered temperature and pressure of the wellbore. Using this information, it is possible to derive a baseline for materials to be used in the wellbore environment.

Before conducting an induced stress analysis for a given cement system, it is important to quantify the mechanical properties of that set cement. Chief among  
25 these properties is the Young's Modulus of elasticity, which is defined by the ratio of axial stress to axial strain. Typically, for a given change in well conditions, the lower the Young's Modulus is for a cement system, the lower the induced stress on that cement will be. Accordingly, the elastic nature exhibited by cement under stress, but

prior to mechanical failure, is as important for long-term annular isolation, as the actual maximum stress at which mechanical failure ultimately occurs. The present invention overcomes the problems associated with a conventional static Young's Modulus test, which is a time-consuming operation and is almost always done with the axial stress applied in a compressive mode—even though by most definitions, the Young's Modulus is a mechanical property pertaining to a materials response under tension.

The following provides a means to combine static flexural/tensile strength testing and elasticity measurements of cements. Since most cements fail in the annulus of a well while under tension, or a combination of tension and compression, the ratio of axial stress to axial strain is an important factor when the axial stress was in tension, or a combination of tension and compression instead of just testing in compression. Using a testing device based on these methods, the present invention can generate Young's Modulus values for different cement compositions under stresses that are similar to the conditions occurring in an actual wellbore. The present invention allows the user to calculate the induced stresses that would occur if the different systems were used in a well, and thus develop better fit for purpose designs.

The present invention includes the development of a testing apparatus that enables the user to first cure from a liquid state, and then determine the mechanical properties such as tensile strength of various cement slurry systems through non-ultrasonic, destructive methods, while maintaining confining pressure and temperature on the cement specimens for the duration of the curing and testing process. It is within the scope of the invention that the present apparatus allows for a more accurate testing of mechanical properties of oil and gas well cements to ensure the long term integrity of the cement sheath in a well bore for the entire operation life of a given well.

Since current ASTM testing is carried out under atmospheric conditions, this invention provides for an alternative means to accurately measure tensile strength of various cement systems under more realistic field conditions. The invention discloses an apparatus that allows for the elimination of data influenced by factors  
5 such as cooldown and depressurization of cured cement samples.

Devices employing the testing techniques of the present invention may be fully automated in such a way that real-time stress versus strain plots can be generated prior to the determination of ultimate mechanical failure values. This would allow for an increase in both the quantity and the quality of data presented to  
10 the clients. Moreover, the present invention provides for data consistency and reliability because a more uniform testing method for all cement systems can be employed and all test conditions and data recording may be microprocessor controlled. The multi-functionality of this apparatus allows the user to measure cement shear bond strength while maintaining confining pressure and temperature.

15

#### **Brief Description of the Drawings**

The accompanying drawings, which are incorporated in and form a part of the specification, illustrate the embodiments of the present invention, and, together with the description, serve to explain the principles of the invention. In the drawings:

20 FIG. 1 is a representative diagram of an embodiment of a modified ASTM testing device that can test tensile strength, or with a different fixture, can test flexural strength;

FIG. 2 is a diagram showing a component of the present invention;

FIG. 3 is a diagram showing a component of the present invention;

25 FIG. 4 is a diagram showing a component of the present invention;

FIG. 5 is top assembly view of an embodiment of the present invention showing the mold body and components;

FIG. 6 is a side assembly view of an embodiment of the present invention showing the mold body and components;

FIG. 7. is top assembly view of another embodiment of the present invention showing a plurality of mold bodies and components;

5        FIG. 8 is a front view of a view of an embodiment of the present invention showing the mold and components in a pressure cylinder;

FIG. 9 is a representative graph showing deflection versus time;

FIG. 10 is a representative graph showing stress versus deflection;

10        FIG. 11 is a representative graph showing Young's Modulus versus deflection;

FIG. 12 is a representative graph showing deflection versus time;

FIG. 13 is a representative graph showing stress versus deflection;

FIG. 14 is a representative graph showing stress versus microstrain;

FIG. 15 is a representative graph showing stress versus deflection;

15        FIG. 16 is a representative graph showing stress versus deflection; and

FIG. 17 is a representative graph showing stress versus deflection

It is to be noted that the drawings illustrate only typical embodiments of the invention and are therefore not to be considered limiting of its scope, for the invention encompasses other equally effective embodiments.

20

#### **Detailed Description of Preferred Embodiment**

Young's Modulus is a measurement of elasticity, which is defined by the ratio of axial stress to axial strain. The elastic nature exhibited by cement under stress, but prior to mechanical failure, is as important for long-term annular isolation, as the actual maximum stress at which mechanical failure ultimately occurs. FIG. 1 shows an embodiment of a flexural/tensile tester 10, which provides a means to combine static flexural/tensile strength testing and elasticity measurements of cements. As

25



configured in the Figure, the tester 10 is configured for testing tensile strength, but can be modified to test flexural strength.

As previously discussed, most cements fail in the annulus of a well while under tension, or a combination of tension and compression. The ratio of axial stress to axial strain is therefore an important factor when the axial stress is in tension, or a combination of tension and compression.

The tester 10 may utilize a beam loading system for automatic testing of cement specimens 11 in flexure and for tensile tests. This tester 10 has a traveling weight 12, which is driven by electric motor across the beam 13 of the tester 10 to produce a constant rate of loading on the specimen 11. The beam 13 has dual scales. As depicted in FIG. 1, the tester 10 is a flexural/tensile tester made by Gilson Company. Those skilled in the art will recognize that any tester capable of flexural and tensile testing is within the scope of the invention. In this embodiment of the tester 10, the traveling weight 12 automatically stops upon specimen 11 failure and load is read directly from the applicable scale on the beam 13.

A sensor 14 is positioned in contact with the tester 10 such that the displacement may be measured and recorded. In the diagram shown herein, a computer 15 records the displacement measurements. This allows for calculations based not only of the force exerted at the time of failure of the specimen 11, but the displacement at the time of failure. The tester 10 provides a constant rate of loading, so the computer 15 may also plot the displacement versus time and/or calculate the loading versus displacement for a variety of calculations. A tester 10 can be used to generate Young's Modulus values for different cement compositions under stresses that are similar to the conditions occurring in an actual wellbore in a pressurized configuration.

The present invention includes the development of a testing apparatus that enables the user to first cure specimens 11 from a liquid state, and then determine the mechanical properties such as tensile strength and stress/strain relationships of

various cement slurry systems through non-ultrasonic, destructive methods, while maintaining confining pressure and temperature on the cement specimens for the duration of the curing and testing process. It is within the scope of the invention that the present apparatus allows for a more accurate testing of mechanical properties of  
5 oil and gas well cements to ensure the long term integrity of the cement sheath in a well bore for the entire operation life of a given well.

As shown in FIG. 2, the cement specimen 11 is poured into a mold 19 having three sections: a mold stationary section 20, a mold floating section 21, and a mold follower section 22. The mold 19 can be inserted into a pressure chamber capable of  
10 simulating the temperature and pressure found in the wellbore environment. Pressures up to 3,000 psi and temperatures up to 500°F can be encountered in this environment. Those skilled in the art will recognize that the current invention is capable of being used at any pressure greater than atmospheric pressure and with a temperature range of about 32°F to about 500°F. By curing and then testing the  
15 specimen 11 under the temperature and pressure conditions found in a wellbore, it is possible to obtain more accurate data related to the strength of the specimen 11. As shown, specimen 11 is poured or formed in a shape similar to the one depicted in FIG. 2.

The follower portion 22 of the mold 19 is bolted or otherwise attached to the  
20 follower 23 at bolt locations 24. Moreover, alignment pins 25 align the mold stationary section 20, a mold floating section 21, and a mold follower section 22. Additionally, the mold stationary section 20 is bolted to the mold base 30, shown in FIG. 3 by base bolts 26. In operation, follower 23 pulls the mold follower section 22 away from the mold stationary section 20 and the mold floating section 21. The  
25 mold floating section 21 is designed to not exert any force of the specimen during testing. The mold stationary section 20, bolted to the mold base 30, remains stationary during testing.

Referring to FIG. 3, the mold base 30 is shown in greater detail. The base bolts 26, which connect the mold base 30 to the stationary section 20 of the mold 19, are shown. Moreover, the mold base 30 is anchored to railings 31. As shown in greater detail below, these railings 31 are anchored to the testing vessel and do not allow any movement.

FIG. 4 shows the cam 40. Cam assembly bolt 41 secures the top and bottom plate of cam 40. The cam 40 pushes against the follower 23 at a front edge 42 of the cam 40. During testing, the cam 40 provides an equal force of pressure against the follower 23, which is imparted on the specimen 11 via the follower section 22 of the mold 19.

The fully assembled mold is shown in FIG. 5. The cement specimen 11 is in the mold stationary section 20, the mold floating section 21, and the mold follower section 22. The follower portion 22 is bolted or otherwise attached to the follower 23 at bolt locations 24. Alignment pins 25 align the mold stationary section 20, the mold floating section 21, and the mold follower section 22. Additionally, the mold stationary section 20 is bolted to the mold base 30, shown in FIG. 3 by base bolts 26.

This assembly view shows how the follower 23 can pull the mold follower section 22 away from the mold stationary section 20 and the mold floating section 21 during testing. The base bolts 26 hold the stationary portion 20 in place as the follower 23 is pushed at the front edge 40 of the cam 40. Cam assembly bolts 41 bolt the cam 40.

This movement is also shown in the side view of the assembly of FIG. 6. The mold stationary section 20, the mold floating section 21, and the mold follower section 22 are shown such that the mold follower section 22 is attached to the follower 23 by bolt 24. The mold stationary section 20 is bolted to the mold base 30 base bolt 26. Cam 40 pushes follower 23, which in turn pulls the mold follower section 22.

Turning to FIG. 7, a plurality of testers are shown connected to the railing 31 within a pressure chamber 80, which is used to simulate the temperature and pressure encountered in the wellbore. Piston 70 is disposed through cover 75 of the pressure chamber 80. The piston 70 is moved by a short stroke hydraulic ram 74 or similar device. Precision linear transducers 71, 72 are positioned on opposite sides of the piston 70 to ensure even travel of the piston 70 in to the pressure chamber 80 and to measure the displacement of the cam. A load cell 73 is disposed therein to measure to the amount of force applied by the ram 74.

A thermocouple 76 and a pressure transducer 77 are connected to the pressure chamber 80. Data from the precision linear transducers 71, 72, the thermocouple 76, and the pressure transducer 77 are provided to a data acquisition unit 78.

Those skilled in the art recognize the benefits of this configuration. Cement specimens 11 are placed in molds 30 within the pressure chamber 80. A pressure medium 79, such as fresh water or mineral oil, is introduced to pressurize the system to the temperature and pressure levels that would be encountered in a wellbore environment. The cement specimens 11 are allowed to cure at these temperatures and pressures, as each would under wellbore conditions. Once cured, each specimen 11 is tested using the ram 74 to push the piston 70 such that each specimen 11 is sequentially stressed until failure.

The piston pushes the first cam until the cement specimen 11 fails. The data acquisition unit 78 constantly monitors the precision linear transducers 71, 72, the thermocouple 76, and the pressure transducer 77, collecting data throughout the process. It is important to arrange each mold with enough axial distance such that the failure of each cement specimen will not cause the next follower to be bumped with a breaking force. By axially spacing the cams such that the first specimen fails, the piston ushers the cam forward to smoothly interface with the next cam. The next sample may be stretched in a sequential fashion .

Once the second specimen fails, another axial gap exists such that the rapid expansion of the cams will not strike the third mold. Though three molds are shown in FIG. 7, those skilled in the art will recognize that any plurality of molds within at least one pressure chamber is considered to be within the scope of the invention.

5           FIG. 8 shows a cross-sectional view of the pressure chamber 80. The pressurizing medium 79 surrounds the testing apparatus. The rails 31 are connected the mold base 30, wherein the pulled portion of the mold 22 is shown on top of the mold base 30. The cam 40 is shown above and below the mold base 30. This arrangement shows how the cam 40 urges the pulled portion of the mold 22 toward  
10       the viewer, thus stressing the cement specimen in the mold until failure.

### Examples

Three cement specimens were cured at atmospheric pressure, 198°F, and 20.0 ppg. The slurry design was used for this experiment was primarily Norcem AS G  
15       with 45% W-10 + 20% MPA-3 + 0.01797 gps CD-31L + 0.0839 pgs R-15L + 0.02 gps FP-6L. A maximum cycle load of 5000 N (2027 psi) was applied.

The deflection versus time graph in FIG. 9 shows the consistency of the deflection of the samples prior to failure. The peaks of the graphs are very similar and the time to failure of the three samples has a similar width on the X-axis.

20           FIG. 10 shows the flexural stress (psi) versus the deflection (inches) for one of these samples. The linear increase of deflection as the stress increased shows the consistency of the results. When the deflection is compared to the Young's Modulus, as shown in FIG. 11, the graph shows the flattening the Young's modulus as the sample's deflection nears the failure point.

25           Two additional samples are shown in FIG. 11 in a tensile strength test. Using the same slurry, a maximum cycle load of 3900 N (878 psi) with an actual failure load of 4725 N (1064 psi) was applied. Again, the consistency of the shape of the peaks and width of the results on the X-axis show the preciseness of the tester in this

analysis. The graph in FIG. 12 shows the tensile stress versus the deflection of the sample under tension only. This is in comparison with FIG. 13 that shows the tensile strength test of the stress versus the microstrain.

In another experiment, Calport H cement was mixed at 16.5 ppg and cured for about 48 hours at atmospheric temperature and pressure. The following table depicts the three specimens as stress using the above-disclosed tester was applied on each specimen. The deflection was measured using the precision linear transducers listed above.

**Table 1: Calport H Stress v. Deflection Testing**

Time (sec)	Deflect 1 (inches)	Stress 1 (psi)	Deflect 2 (inches)	Stress 2 (psi)	Deflect 3 (inches)	Stress 3 (psi)
0	0	0	0	0	0	0
1.002	0	0	0	0	0	0
1.998	0	0	0	0	0	-5.775096
3.000	0	0	0	0	0	0
4.002	0	0	0	0	0	0
4.998	0	0	0	0	0	0
6.000	0	0	0	0	0	5.775096
7.000	0	5.775096	0	11.550184	0	5.775096
8.000	0	5.775096	0	11.550184	0	11.550184
9.000	0	11.550192	0	11.550184	0	11.550184
10.000	0	17.32528	0	17.32528	0	17.32528
11.000	0	17.32528	0	17.32528	0	17.32528
12.000	0	23.100376	0	23.100376	0	23.100376
13.000	0	23.100376	0	28.875464	0.0001	28.875472
14.000	0	28.875472	0	28.875464	0	28.875472
15.000	0	28.875472	0	28.875464	0.0001	28.875472
16.000	0	28.875472	0	34.6505616	0.0001	34.65056
17.000	0	34.650568	0	34.6505616	0.0001	34.65056
18.000	0	34.650568	0	40.425656	0.0001	34.65056
19.000	0	34.650568	0	40.425656	0.0001	34.65056
20.000	0	40.425656	0	40.425656	0.0001	40.4256576
21.000	0	40.425656	0	46.2007504	0.0001	46.200752
22.000	0	40.425656	0	46.2007504	0.0001	46.200752
23.000	0	46.2007536	0.0001	51.975848	0.0001	51.9758464
24.000	0.0001	46.2007536	0.0001	51.975848	0.0001	57.750944
25.000	0.0001	51.975848	0.0001	57.750936	0.0001	57.750944
26.000	0.0001	51.975848	0.0001	57.750936	0.0005	63.526032
27.000	0.0001	57.7509424	0.0001	63.526032	0.0006	69.301128

<b>Time</b>	<b>Deflect 1</b>	<b>Stress 1</b>	<b>Deflect 2</b>	<b>Stress 2</b>	<b>Deflect 3</b>	<b>Stress 3</b>
28.000	0.0001	57.7509424	0.0001	63.526032	0.0008	69.301128
29.000	0.0001	63.52604	0.0004	63.526032	0.0009	69.301128
30.000	0.0001	63.52604	0.0004	69.301128	0.001	75.076224
31.000	0.0001	69.301128	0.0005	69.301128	0.0012	75.076224
32.000	0.0001	75.076224	0.0006	75.076224	0.0013	80.85132
33.000	0.0001	75.076224	0.0007	75.076224	0.0014	80.85132
34.000	0.0004	75.076224	0.0008	80.851312	0.0016	86.626408
35.000	0.0004	75.076224	0.0009	86.626408	0.0017	92.401504
36.000	0.0005	80.85132	0.001	92.401504	0.0018	92.401504
37.000	0.0006	80.85132	0.0011	92.401504	0.002	98.1766
38.000	0.0007	86.626416	0.0013	92.401504	0.0021	98.1766
39.000	0.0008	92.401504	0.0013	98.1766	0.0023	103.951696
40.000	0.001	92.401504	0.0015	98.1766	0.0024	103.951696
41.000	0.001	98.1766	0.0015	103.951696	0.0025	103.951696
42.000	0.0012	103.951696	0.0017	103.951696	0.0026	109.726792
43.000	0.0013	103.951696	0.0017	109.726784	0.0027	115.50188
44.000	0.0013	103.951696	0.0019	109.726784	0.0029	115.50188
45.000	0.0015	109.726792	0.0019	115.50188	0.003	121.276976
46.000	0.0016	109.726792	0.0021	115.50188	0.0031	121.276976
47.000	0.0017	115.501888	0.0021	121.276984	0.0033	121.276976
48.000	0.0019	121.276976	0.0022	121.276984	0.0034	127.05208
49.000	0.002	121.276976	0.0024	127.052104	0.0035	127.05208
50.000	0.0021	127.052072	0.0024	132.827144	0.0037	138.60224
51.000	0.0022	127.052072	0.0026	132.827144	0.0038	138.60224
52.000	0.0023	127.052072	0.0027	132.827144	0.004	138.60224
53.000	0.0025	132.827176	0.0028	138.602264	0.0041	138.60224
54.000	0.0025	132.827176	0.0029	138.602264	0.0042	144.37736
55.000	0.0027	144.377336	0.0031	144.377384	0.0043	150.15248
56.000	0.0028	144.377336	0.0031	150.152424	0.0044	155.92752
57.000	0.003	144.377336	0.0033	150.152424	0.0045	155.92752
58.000	0.0031	144.377336	0.0034	150.152424	0.0047	155.92752
59.000	0.0031	150.152456	0.0036	155.927544		
60.000	0.0033	155.927576	0.0036	155.927544		
61.000			0.0038	161.702664		
62.000			0.0039	161.702664		
63.000			0.0041	167.477704		
64.000			0.0042	167.477704		

As shown in this table, the first and third specimens bear similar results, namely 155.927 psi with 0.0033 inches deflection and 0.0047 inches deflection, respectively while the second specimen bears 167.478 psi and 0.0042 inches

deflection. The data for the second and third specimens have been graphed in FIG. 15. The closeness of this data indicates the consistency of the testing technique. It is envisioned that this consistency will be seen in pressurized experiments.

In another experiment, Calport G cement was mixed at 15.8 ppg and cured  
5 for about 48 hrs at 130°F and atmospheric pressure. Two specimens were tested:

**Table 2: Calport G Stress v. Deflection Testing**

<b>Time</b> (sec)	<b>Deflect 2</b> (inches)	<b>Stress 2</b> (psi)	<b>Deflect 1</b>	<b>Stress 1</b> (psi)
1	0	21.787232	0	21.787232
2	0	21.787232	0	21.787232
3	0	21.787232	0	21.787232
4	0	21.787232	0	21.787232
5	0	21.787232	0	21.787232
6	0	21.787232	0	21.787232
7	0	21.787232	0	21.787232
8	0	21.787232	0	21.787232
9	0	21.787232	0	21.787232
10	0	27.23404	0	21.787232
11	0	32.680856	0	27.23404
12	0	32.680856	0	27.23404
13	0	38.127664	0	32.680856
14	0	43.574472	0	38.127664
15	0	43.574472	0	38.127664
16	0	43.574472	0	43.574472
17	0	49.02128	0	43.574472
18	0	49.02128	0	43.574472
19	0	49.02128	0	43.574472
20	0	54.468088	0	49.02128
21	0	59.914896	0	54.468088
22	0	59.914896	0	54.468088
23	0	59.914896	0	59.914896
24	0	65.361704	0	59.914896
25	0	65.361704	0	59.914896
26	0	70.808512	0	65.361704
27	0	70.808512	0	65.361704
28	0	76.25532	0	70.808512
29	0	76.25532	0	70.808512
30	0	81.70216	0	76.25532
31	0	81.70216	0	76.25532



Time	Deflect 2	Stress 2	Deflect 1	Stress 1
32	0	81.70216	0	81.70216
33	0	87.14896	0	81.70216
34	0	87.14896	0	87.14896
35	0	92.59576	0	87.14896
36	0	98.04256	0	92.59576
37	0	98.04256	0	92.59576
38	0	98.04256	0	98.04256
39	0	103.48936	0	98.04256
40	0	103.48936	0	98.04256
41	0	108.93616	0	98.04256
42	0.0001	108.93616	0	103.48936
43	0.0001	114.38296	0	103.48936
44	0.0001	114.38296	0	108.93616
45	0.0001	119.82976	0	108.93616
46	0.0001	119.82976	0	114.38296
47	0.0001	125.27656	0	114.38296
48	0.0001	125.27656	0	119.82976
49	0.0004	130.72344	0	119.82976
50	0.0005	136.17024	0	119.82976
51	0.0005	136.17024	0	125.27656
52	0.0005	136.17024	0	125.27656
53	0.0006	141.61704	0.0001	130.72344
54	0.0007	147.06384	0.0001	136.17024
55	0.0007	147.06384	0.0001	136.17024
56	0.0008	152.51064	0.0001	141.61704
57	0.0009	152.51064	0.0009	147.06384
58	0.0009	157.95744	0.001	147.06384
59	0.001	157.95744	0.001	152.51064
60	0.001	163.40424	0.001	152.51064
61	0.0011	163.40424	0.001	152.51064
62	0.0011	168.85104	0.001	157.95744
63	0.0012	168.85104	0.001	157.95744
64	0.0013	174.29784	0.001	163.40424
65	0.0013	174.29784	0.0013	163.40424
66	0.0014	179.74472	0.0013	168.85104
67	0.0015	179.74472	0.0013	174.29784
68	0.0016	185.19152	0.0013	174.29784
69	0.0017	185.19152	0.0014	174.29784
70	0.0017	185.19152	0.0014	179.74472
71	0.0018	185.19152	0.0015	185.19152
72	0.0019	190.63832	0.0015	185.19152
73	0.0019	190.63832	0.0016	185.19152
74	0.002	196.08512	0.0016	185.19152

<b>Time</b>	<b>Deflect 2</b>	<b>Stress 2</b>	<b>Deflect 1</b>	<b>Stress 1</b>
75	0.0021	196.08512	0.0017	185.19152
76	0.0022	201.53192	0.0017	190.63832
77	0.0023	201.53192	0.0018	196.08512
78	0.0023	206.97872	0.0019	196.08512
79	0.0024	206.97872	0.002	201.53192
80	0.0025	212.42552	0.002	201.53192
81	0.0026	212.42552	0.0021	201.53192
82	0.0027	212.42552	0.0022	206.97872
83	0.0028	217.87232	0.0022	212.42552
84	0.0028	217.87232	0.0023	212.42552
85	0.0029	223.3192	0.0023	212.42552
86	0.003	223.3192	0.0025	217.87232
87	0.0031	228.766	0.0025	217.87232
88	0.0032	228.766	0.0026	223.3192
89	0.0032	228.766	0.0027	223.3192
90	0.0033	234.2128	0.0027	223.3192
91	0.0034	234.2128	0.0028	228.766
92	0.0035	239.6596	0.0029	228.766
93	0.0036	239.6596	0.003	234.2128
94	0.0037	239.6596	0.0031	234.2128
95	0.0038	245.1064	0.0032	239.6596
96	0.0039	250.5532	0.0032	239.6596
97	0.0039	250.5532	0.0033	239.6596
98	0.0041	250.5532	0.0034	245.1064
99	0.0041	256	0.0035	250.5532
100	0.0042	256	0.0036	250.5532
101	0.0043	256	0.0037	250.5532
102	0.0044	261.4468	0.0038	256
103	0.0045	261.4468	0.0039	256
104	0.0046	266.8936	0.004	261.4468
105	0.0047	266.8936	0.004	261.4468
106	0.0048	266.8936	0.0042	266.8936
107	0.0049	272.3404	0.0042	266.8936
108	0.005	272.3404	0.0044	266.8936
109	0.0051	277.7872	0.0044	272.3404
110	0.0052	277.7872	0.0046	272.3404
111	0.0053	277.7872	0.0046	272.3404
112	0.0054	283.23408	0.0047	277.7872
113	0.0055	283.23408	0.0048	277.7872
114	0.0056	288.68088	0.0049	283.23408
115	0.0057	288.68088	0.005	283.23408
116	0.0058	294.12768	0.0051	288.68088
117	0.0059	294.12768	0.0052	288.68088

<b>Time</b>	<b>Deflect 2</b>	<b>Stress 2</b>	<b>Deflect 1</b>	<b>Stress 1</b>
118	0.006	294.12768	0.0053	294.12768
119	0.0061	294.12768	0.0054	294.12768
120	0.0062	299.57448	0.0055	294.12768
121	0.0063	305.02128	0.0056	299.57448
122	0.0064	305.02128	0.0058	299.57448
123	0.0065	305.02128	0.0058	305.02128
124	0.0066	310.46808	0.006	305.02128
125	0.0067	310.46808	0.006	305.02128
126	0.0068	315.91488	0.0062	310.46808
127	0.0069	315.91488	0.0062	310.46808
128	0.007	315.91488	0.0064	315.91488
129	0.0071	321.36168	0.0064	315.91488
130	0.0072	326.80856	0.0067	315.91488
131	0.0073	326.80856	0.0067	321.36168
132	0.0074	326.80856	0.0069	326.80856
133	0.0075	326.80856	0.007	326.80856
134	0.0076	332.25536	0.0072	326.80856
135	0.0077	332.25536	0.0073	332.25536
136	0.0078	332.25536	0.0074	332.25536
137	0.0079	337.70216	0.0075	332.25536
138	0.008	343.14896	0.0076	337.70216
139	0.0081	343.14896	0.0078	337.70216
140	0.0082	348.59576	0.0079	343.14896
141	0.0083	348.59576	0.0081	348.59576
142	0.0084	348.59576	0.0083	348.59576
143	0.0086	348.59576	0.0085	348.59576
144	0.0087	348.59576	0.0086	348.59576
145	0.0088	348.59576	0.0088	348.59576
146	0.0089	348.59576	0.0093	348.59576
147	0.0091	354.04256	0.0093	348.59576
148	0.0092	359.48936	0.0097	354.04256
149	0.0093	359.48936	0.0098	354.04256
150	0.0094	364.93616	0.0102	359.48936
151	0.0096	364.93616	0.0104	359.48936
152	0.0097	364.93616	0.0107	364.93616
153	0.0098	370.38296	0.0111	364.93616
154	0.0099	370.38296	0.0114	364.93616
155	0.0101	370.38296	0.0119	364.93616
156	0.0102	375.82976	0.0125	370.38296
157	0.0103	375.82976	0.0126	370.38296
158	0.0104	381.27664	0.0134	370.38296
159	0.0106	381.27664	0.0136	375.82976
160	0.0107	386.72344	0.0142	381.27664

Time	Deflect 2	Stress 2	Deflect 1	Stress 1
161	0.0109	386.72344	0.0146	381.27664
162	0.011	386.72344		
163	0.0111	392.17024		
164	0.0113	392.17024		
165	0.0114	392.17024		
166	0.0115	397.61704		
167	0.0116	397.61704		
168	0.0118	397.61704		
169	0.0119	403.06384		
170	0.012	403.06384		
171	0.0121	408.51064		
172	0.0122	408.51064		
173	0.0124	408.51064		
174	0.0125	413.95744		
175	0.0126	413.95744		
176	0.0126	419.40424		
177	0.0128	419.40424		
178	0.0129	419.40424		
179	0.013	424.85104		
180	0.0131	424.85104		
181	0.0132	430.29792		
182	0.0133	430.29792		
183	0.0134	430.29792		
184	0.0135	430.29792		
185	0.0136	435.74464		

As shown in this table, the first specimen bore 381.276 psi and 0.0146 inches deflection while the second specimen bore 435.745 psi and 0.0136 inches deflection. The data for the first and second specimens have been graphed in FIG. 16. The closeness of this data indicates the consistency of the testing technique. It is envisioned that this consistency will be seen in pressurized experiments.

In another experiment, Calport G cement was mixed at 15.8 ppg and cured for about 48 hrs at 130°F and atmospheric pressure. Two specimens were tested.

**Table 3: Second Calport G Stress v. Deflection Testing**

Time (sec)	Deflection 2 (inches)	Stress 2 (psi)	Deflection 1 (inches)	Stress 1 (psi)
0	0.000	10.894	0.0000	21.79
1.000	0.000	10.894	0.0000	21.79

Time	Deflection 2	Stress 2	Deflection 1	Stress 1
2.000	0.000	10.894	0.0000	21.79
3.000	0.000	16.340	0.0000	21.79
4.000	0.000	16.340	0.0000	21.79
5.000	0.000	16.340	0.0000	21.79
6.000	0.000	16.340	0.0000	21.79
7.000	0.000	21.787	0.0000	27.23
8.000	0.000	21.787	0.0000	27.23
9.000	0.000	21.787	0.0000	32.68
10.000	0.000	21.787	0.0000	38.13
11.000	0.000	27.234	0.0000	38.13
12.000	0.000	27.234	0.0000	43.57
13.000	0.000	27.234	0.0000	49.02
14.000	0.000	32.681	0.0000	49.02
15.000	0.000	38.128	0.0000	49.02
16.000	0.000	38.128	0.0000	54.47
17.000	0.001	43.574	0.0000	54.47
18.000	0.001	43.574	0.0000	59.91
19.000	0.001	49.021	0.0000	59.91
20.000	0.001	54.468	0.0000	59.91
21.000	0.001	59.915	0.0000	59.91
22.000	0.001	59.915	0.0000	65.36
23.000	0.001	65.362	0.0000	70.81
24.000	0.001	70.809	0.0000	76.26
25.000	0.001	70.809	0.0000	76.26
26.000	0.001	76.255	0.0000	76.26
27.000	0.001	81.702	0.0001	76.26
28.000	0.001	81.702	0.0001	81.70
29.000	0.001	81.702	0.0001	87.15
30.000	0.001	87.149	0.0001	87.15
31.000	0.001	87.149	0.0001	87.15
32.000	0.001	92.596	0.0001	92.60
33.000	0.001	98.043	0.0001	98.04
34.000	0.002	98.043	0.0001	98.04
35.000	0.002	103.489	0.0001	98.04
36.000	0.002	103.489	0.0001	98.04
37.000	0.002	108.936	0.0001	103.49
38.000	0.002	114.383	0.0001	108.94
39.000	0.002	114.383	0.0003	114.38
40.000	0.002	119.830	0.0004	114.38
41.000	0.002	119.830	0.0005	114.38
42.000	0.002	119.830	0.0006	119.83
43.000	0.002	119.830	0.0006	119.83
44.000	0.002	125.277	0.0007	125.28

Time	Deflection 2	Stress 2	Deflection 1	Stress 1
45.000	0.002	130.723	0.0007	125.28
46.000	0.002	130.723	0.0008	136.17
47.000	0.002	136.170	0.0008	136.17
48.000	0.002	136.170	0.0009	136.17
49.000	0.002	141.617	0.0010	136.17
50.000	0.003	141.617	0.0011	136.17
51.000	0.003	147.064	0.0012	136.17
52.000	0.003	147.064	0.0013	147.06
53.000	0.003	152.511	0.0014	147.06
54.000	0.003	152.511	0.0015	152.51
55.000	0.003	152.511	0.0016	152.51
56.000	0.003	157.957	0.0017	157.96
57.000	0.003	157.957	0.0018	157.96
58.000	0.003	163.404	0.0019	163.40
59.000	0.003	163.404	0.0020	163.40
60.000	0.003	168.851	0.0021	168.85
61.000	0.003	168.851	0.0022	168.85
62.000	0.003	174.298	0.0023	174.30
63.000	0.003	174.298	0.0025	174.30
64.000	0.004	179.745	0.0026	179.74
65.000	0.004	179.745	0.0027	179.74
66.000	0.004	185.192	0.0028	179.74
67.000	0.004	185.192	0.0029	185.19
68.000	0.004	190.638	0.0031	190.64
69.000	0.004	190.638	0.0032	190.64
70.000	0.004	190.638	0.0033	190.64
71.000	0.004	196.085	0.0035	196.09
72.000	0.004	196.085	0.0035	196.09
73.000	0.004	196.085	0.0037	201.53
74.000	0.004	201.532	0.0038	201.53
75.000	0.004	201.532	0.0038	201.53
76.000	0.004	206.979	0.0041	206.98
77.000	0.004	206.979	0.0041	206.98
78.000	0.005	212.426	0.0043	212.43
79.000	0.005	212.426	0.0043	212.43
80.000	0.005	212.426	0.0045	212.43
81.000	0.005	217.872	0.0045	217.87
82.000	0.005	217.872	0.0047	217.87
83.000	0.005	223.319	0.0048	223.32
84.000	0.005	223.319	0.0049	223.32
85.000	0.005	223.319	0.0050	223.32
86.000	0.005	228.766	0.0052	228.77
87.000	0.005	228.766	0.0052	228.77

Time	Deflection 2	Stress 2	Deflection 1	Stress 1
88.000	0.005	234.213	0.0054	234.21
89.000	0.005	234.213	0.0055	234.21
90.000	0.006	234.213	0.0056	234.21
91.000	0.006	239.660	0.0057	239.66
92.000	0.006	239.660	0.0058	239.66
93.000	0.006	245.106	0.0059	245.11
94.000	0.006	245.106	0.0060	250.55
95.000	0.006	250.553	0.0062	250.55
96.000	0.006	250.553	0.0063	250.55
97.000	0.006	250.553	0.0063	250.55
98.000	0.006	256.000	0.0065	256.00
99.000	0.006	256.000	0.0066	256.00
100.000	0.006	261.447	0.0068	261.45
101.000	0.006	261.447	0.0069	261.45
102.000	0.007	261.447	0.0071	266.89
103.000	0.007	266.894	0.0071	266.89
104.000	0.007	272.340	0.0074	266.89
105.000	0.007	272.340	0.0075	272.34
106.000	0.007	272.340	0.0077	272.34
107.000	0.007	277.787	0.0079	272.34
108.000	0.007	283.234	0.0080	277.79
109.000	0.007	283.234	0.0084	277.79
110.000	0.007	283.234	0.0086	277.79
111.000	0.007	283.234	0.0090	283.23
112.000	0.008	283.234	0.0092	283.23
113.000	0.008	283.234	0.0097	288.68
114.000	0.008	288.681	0.0099	288.68
115.000	0.008	288.681	0.0103	288.68
116.000	0.008	294.128	0.0106	294.13
117.000	0.008	294.128	0.0110	294.13
118.000	0.008	294.128	0.0112	294.13
119.000	0.008	299.574	0.0116	299.57
120.000	0.009	299.574	0.0117	305.02
121.000	0.009	299.574	0.0122	305.02
122.000	0.009	305.021	0.0123	305.02
123.000	0.009	305.021	0.0125	305.02
124.000	0.009	310.468	0.0127	305.02
125.000	0.009	310.468	0.0130	310.47
126.000	0.010	310.468	0.0131	310.47
127.000	0.010	315.915	0.0135	315.91
128.000	0.010	315.915	0.0136	315.91
129.000	0.010	315.915	0.0138	315.91
130.000	0.010	321.362	0.0139	321.36

Time	Deflection 2	Stress 2	Deflection 1	Stress 1
131.000	0.011	321.362	0.0141	326.81
132.000	0.011	326.809	0.0142	326.81
133.000	0.011	326.809	0.0144	326.81
134.000	0.011	332.255	0.0145	332.26
135.000	0.011	332.255	0.0147	332.26
136.000	0.012	332.255	0.0149	332.26
137.000	0.012	337.702	0.0149	332.26
138.000	0.012	337.702	0.0152	337.70
139.000	0.012	337.702	0.0153	337.70
140.000	0.012	343.149	0.0155	343.15
141.000	0.012	348.596	0.0156	343.15
142.000	0.013	348.596	0.0157	348.60
143.000	0.013	348.596	0.0158	348.60
144.000	0.013	348.596	0.0160	348.60
145.000	0.013	354.043	0.0161	348.60
146.000	0.013	354.043	0.0163	354.04
147.000	0.013	359.489	0.0164	359.49
148.000	0.013	359.489	0.0166	359.49
149.000	0.014	364.936	0.0167	359.49
150.000	0.014	364.936	0.0168	364.94
151.000	0.014	364.936	0.0169	364.94
152.000	0.014	370.383	0.0171	370.38
153.000	0.014	370.383	0.0172	370.38
154.000	0.014	370.383	0.0173	370.38
155.000	0.014	375.830	0.0175	370.38
156.000	0.014	375.830	0.0176	370.38
157.000	0.015	381.277	0.0177	375.83
158.000	0.015	381.277	0.0178	375.83
159.000	0.015	381.277	0.0179	381.28
160.000	0.015	386.723	0.0180	381.28
161.000	0.015	386.723	0.0181	386.72
162.000	0.015	386.723	0.0182	386.72
163.000	0.015	392.170	0.0183	386.72
164.000	0.015	392.170	0.0185	392.17
165.000	0.015	397.617	0.0185	392.17
166.000	0.016	397.617	0.0187	392.17
167.000	0.016	397.617	0.0187	397.62
168.000	0.016	403.064		
169.000	0.016	403.064		
170.000	0.016	403.064		
171.000	0.016	408.511		
172.000	0.016	408.511		
173.000	0.016	408.511		



Time	Deflection 2	Stress 2	Deflection 1	Stress 1
174.000	0.016	413.957		
175.000	0.016	413.957		
176.000	0.016	413.957		
177.000	0.017	419.404		
178.000	0.017	419.404		
179.000	0.017	419.404		
180.000	0.017	424.851		
181.000	0.017	424.851		
182.000	0.017	430.298		
183.000	0.017	430.298		
184.000	0.017	430.298		
185.000	0.017	435.745		
186.000	0.017	435.745		
187.000	0.018	441.192		
188.000	0.018	441.192		
189.000	0.018	441.192		
190.000	0.018	446.638		
191.000	0.018	446.638		

As shown in this table, the first specimen bore 397.62 psi and 0.0187 inches deflection while the second specimen bore 446.638 psi 0.018 inches deflection. The data for the first and second specimens have been graphed in FIG. 17. Again, the closeness of this data indicates the consistency of the testing technique. It is envisioned that this consistency will be seen in pressurized experiments.

Those skilled in the art will recognize that the present testing method and apparatus are applicable to any type of cement or cement composition. Examples of suitable hydraulic cement types that may be employed, alone or in mixtures, for wellbore cementing include Portland cements, and more particularly ASTM Type I, II, III, IV and/or V Portland cements, and API Class A, B, C, G and/or H Portland cements, pozzolan cements, Portland cement blends, commercial lightweight cements, slag cements, and microfine cements. Any natural or synthetic material that is substantially elastic, and more particularly that is selected to be substantially elastic under in situ cementing conditions (e.g., downhole well cementing conditions), may be employed. Such materials may be employed in particulate form,

and may have individual particles of material may have shapes such as beaded, regular, or irregular shapes, or mixtures thereof. Examples of substantially elastic materials include, but are not limited to, those elastic materials having a Young's modulus of elasticity between about 500 psi and about 2,600,000 psi at anticipated cementing conditions, alternatively between about 500 psi and about 2,000,000 psi at anticipated cementing conditions, alternatively between about 5,000 psi and about 2,000,000 psi at anticipated cementing conditions, alternatively between about 5,000 psi and about 500,000 psi at anticipated cementing conditions, alternatively between about 5,000 psi and 200,000 psi at anticipated cementing conditions, and further alternatively between about 7,000 and 150,000 psi at anticipated cementing conditions. Other examples of substantially elastic materials include, but are not limited to, those elastic materials having a Young's modulus of elasticity between about 500 psi and about 30,000,000 psi at anticipated cementing conditions, alternatively between about 2,000,000 psi and about 30,000,000 psi at anticipated cementing conditions, alternatively between about 2,000,000 psi and about 10,000,000 psi at anticipated cementing conditions, alternatively between about 5,000 psi and about 5,000,000 psi at anticipated cementing conditions, and alternatively between about 7,000 psi and about 1,500,000 psi at anticipated cementing conditions. Yet other examples of substantially elastic materials include, but are not limited to, those elastic materials having a Young's modulus of elasticity between about 500 psi and about 150,000 psi at anticipated cementing conditions. Substantially elastic materials may also have values of Young's modulus of elasticity that are greater than or lesser than those values given in the ranges above.

Having described the invention above, various modifications of the techniques, procedures, material and equipment will be apparent to those in the art. It is intended that all such variations within the scope and spirit of the appended claims be embraced thereby.